

PRODUCT INFORMATION

ULTIMEG 2020

2 PART EPOXIDE
AMBIENT CURED
TRICKLE IMPREGNATION
CLASS H (180°C)

ULTIMEG 2020 TWO PART EPOXY TRICKLE RESIN

GENERAL DESCRIPTION

Ultimeg 2020 is a two-component epoxide resin that features high bond strength at all temperatures up to 180°C Class H. The system is applied by trickle methods at ambient or slightly elevated temperatures to give good penetration and excellent fill of the winding. The cured films have excellent electrical properties together with resistance to atmospheric moisture and chemical attack.

APPLICATION

For trickle impregnating of motor armature and stators together with the encapsulation, sealing and potting of small electronic and electrical components.

SPECIFICATION

PROPERTIES OF THE BASE -

Viscosity @ 25°C	poise	20 – 25
Specific gravity		1.13 – 1.17
Appearance		clear

PROPERTIES OF THE HARDENER -

Viscosity @ 25°C	poise	0.5
Specific gravity		0.98 - 1.00
Appearance		Clear liquid

PROPERTIES OF THE MIXTURE -

Mix ratio base: hardener		5:1 pbw 4.3:1 pbv
Viscosity @ 25°C	poise	2 - 6
Specific gravity		1.10 – 1.14
Usable life 100 grams mass		30 minutes

ULTIMEG 2020

WORKSHOP PRACTICE

Most problems occur with 2 part systems due to the failure to mix correctly. The following procedure is recommended: -

The stirring process should scrape the bottom and the sides of the container and be sufficient to ensure there are no dead areas of unmixed material but should also be a relatively slow process stirring a horizontal circular motion so that minimal air is included into the mix. The base and hardener can be measure out by weight, volume or by using all of the pre-weighed kit, but it should be noted the usable life of the mixture decreases as the weight of the mix increases. Ensure the base and hardener are mixed thoroughly using the minimal air inclusion method described previously. This mixing process can take up to 4-5 minutes, and it is recommended that, if the usable life allows, extra time is spent mixing at this stage where failure to mix is most frequent.

For non-rotational and rotational or trickle impregnating of motor armature and stators, the component to be treated is normally processed at a temperature of 60-80°C although this temperature can be varied according to component size.

2020 Mixture is slowly poured on to the heated component, and gelation takes place whilst impregnation is in progress.

In order to develop maximum properties it is recommended that the U2020 be warmed to 50°C. Heat cured samples will exhibit a superior appearance as the material can have a slight surface tack unless it is warmed whilst it is allowed to cure.

CURE SCHEDULE

24 hours @ 25°C

6 hours @ 50°C

PACKAGING

1kg, and 5 kg kit

ULTIMEG 2020

PROPERTIES OF CURED COMPOUND

Shore D hardness	DIN 53505	88	
Thermal Class	ASTM D2307/20,000hrs	180	°c
Deflection temperature	IEC1006	115	°c
Bond strength	ASTM D2519	25	kg
Tensile strength	ISO 527	85	N/mm ²
Elongation at break	ISO 527	2	%
Thermal Conductivity	ISO 8894-1	0.22	W/M/K
Dielectric strength – Dry	ASTM D115	110	Kv/mm
Dielectric strength – Wet	ASTM D115	82	Kv/mm
Dielectric constant	IEC 250	4.31	@ 50Hz
Dissipation factor	IEC 250	3%	@ 50Hz
Volume resistivity	IEC 93	> 10 ¹³	ohm/cm
Comparative Tracking Index	IEC 112	>550	V

STORAGE

24 months shelf life, stored between 10°C and 30°C.

HEALTH & SAFETY

See relevant Material Safety Data Sheet.

AEV Limited Issue no. 5 Date: 11.11