

VIDAFLEX S350 UL

Composition

VIDAFLEX S350: Silicone elastomer coated knitted "E"- glass insulating sleeving.

VIDAFLEX S350 insulating sleevings offer a high degree of flexibility and they provide a good resistance against ozone, ultraviolet radiation and humidity.

VIDAFLEX S350 are UL recognized components (UL-File: E154100(M)).

VIDAFLEX S350 insulating sleevings are compliant to the requirements of the directive 2002/95/EC (RoHS).

Max. short term temperature: 250°C.

Application

Protection and insulation of leads and wiring harness in household appliances, lamps and vehicles.

Insulation of the internal wiring of electrical motors.

Bore size (mm)	Nom. wall thickness (mm)	Weight approx. (g/m)	Breakthrough voltage at RT (kV)
3,0 ± 0,15	1,0	12	≥7,0
4,0 ± 0,2	1,0	16	≥ 7,0
5,0 ±0,2	1,0	19	≥ 7,0
6,0 ± 0,25	1,0	22	≥ 7,0
7,0 ± 0,25	1,0	25	≥ 7,0
8,0 ± 0,25	1,0	29	≥ 7,0
9,0 ± 0,3	1,0	33	≥ 7,0
10,0 ± 0,3	1,0	37	≥ 7,0
12,0 ± 0,3	1,0	44	≥ 7,0
14,0 ± 0,4	1,0	53	≥ 7,0
16,0 ± 0,4	1,0	64	≥ 7,0
18,0 ± 0,5	1,0	75	≥ 7,0
20,0 ± 0,5	1,0	88	≥ 7,0
22,0 ± 0,5	1,0	105	≥ 7,0
24,0 ± 0,5	1,0	116	≥ 7,0
25,0 ± 0,5	1,4	122	≥ 7,0
Measurement according to EN 60684-2			
Availability			
Standard roll length 250, 100, 50 and 25 m sp		5 m spools, dependant on bore si	ize. Cut to length on request.
Colour	Colour Black		

Thermal Class 180 (Class H) according to IEC 60085

All values stated are to be seen as typical values. We reserve the right to introduce changes within the framework of further technical development. We do not accept any obligations or liabilities in respect of this information. Status: 01/2009 KREMPEL GmbH · Papierfabrikstrasse 4 · D-71665 Vaihingen / Enz · Tel. +49 (0) 7042 915-0 · E-mail: info@krempel-group.com

Electrical Insulations Elektroisolierstoffe

Composites Verbundwerkstoffe Base Materials Basismaterialien